

**A240/A240M – 20a**

**TABLE 2 Mechanical Test Requirements**

UNS Designation	Type <sup>A</sup>	Tensile Strength, min		Yield Strength, <sup>B</sup> min		Elongation in 2 in. or 50 mm, min, %	Hardness, max <sup>C</sup>		Cold Bend <sup>D</sup>
		ksi	MPa	ksi	MPa		Brinell, HBW	Rockwell	
		Austenitic (Chromium-Nickel)		(Chromium-Manganese-Nickel)					
N08020	...	80	550	35	240	30 <sup>F</sup>	217	95 HRBW	not required
N08367									
Sheet and Strip		100	690	45	310	30	...	100 HRBW	not required
Plate		95	655	45	310	30	241	...	not required
N08700	...	80	550	35	240	30	192	90 HRBW	not required
N08800	800 <sup>F</sup>	75	520	30 <sup>G</sup>	205 <sup>G</sup>	30 <sup>H</sup>	...	...	not required
N08810	800H <sup>F</sup>	65	450	25 <sup>G</sup>	170 <sup>G</sup>	30	...	...	not required
N08811	...	65	450	25	170	30	...	...	not required
N08904	904L <sup>F</sup>	71	490	31	220	35	...	90 HRBW	not required
N08925	...	87	600	43	295	40	...	...	not required
N08926	...	94	650	43	295	35	...	...	not required
S20100	201-1 <sup>I</sup>	75	515	38	260	40	217	95 HRBW	...
S20100	201-2 <sup>I</sup>	95	655	45	310	40	241	100 HRBW	...
S20103	201L <sup>F</sup>	95	655	38	260	40	217	95 HRBW	not required
S20153	201LN <sup>F</sup>	95	655	45	310	45	241	100 HRBW	not required
S20161	...	125	860	50	345	40	255	25 HRC	not required
S20200	202	90	620	38	260	40	241	...	...
S20400	...	95	655	48	330	35	241	100 HRBW	not required
S20431	...	90	620	45	310	40	241	100 HRBW	not required
S20432	...	75	515	30	205	40	201	92 HRBW	not required
S20433	...	80	550	35	240	40	217	95 HRBW	not required
S20910	XM-19 <sup>J</sup>								
Sheet and Strip		105	725	60	415	30	241	100 HRBW	not required
Plate		100	690	55	380	35	241	100 HRBW	not required
S21600	XM-17 <sup>J</sup>								
Sheet and Strip		100	690	60	415	40	241	100 HRBW	not required
Plate		90	620	50	345	40	241	100 HRBW	not required
S21603	XM-18 <sup>J</sup>								
Sheet and Strip		100	690	60	415	40	241	100 HRBW	not required
Plate		90	620	50	345	40	241	100 HRBW	not required
S21640	...	95	650	45	310	40	...	...	not required
S21800	...	95	655	50	345	35	241	100 HRBW	not required
S21904	XM-11 <sup>J</sup>								
Sheet and Strip		100	690	60	415	40	241	100 HRBW	not required
Plate		90	620	50	345	45	241	100 HRBW	not required
S24000	XM-29 <sup>J</sup>								
Sheet and Strip		100	690	60	415	40	241	100 HRBW	not required
Plate		100	690	55	380	40	241	100 HRBW	not required
S30100	301	75	515	30	205	40	217	95 HRBW	not required
S30103	301L <sup>F</sup>	80	550	32	220	45	241	100 HRBW	not required
S30153	301LN <sup>F</sup>	80	550	35	240	45	241	100 HRBW	not required
S30200	302	75	515	30	205	40	201	92 HRBW	not required
S30400	304	75	515	30	205	40	201	92 HRBW	not required
S30403	304L	70	485	25	170	40	201	92 HRBW	not required
S30409	304H	75	515	30	205	40	201	92 HRBW	not required
S30415	...	87	600	42	290	40	217	95 HRBW	not required
S30435	...	65	450	23	155	45	187	90 HRBW	...
S30441	...	75	515	30	205	40	201	92 HRBW	not required
S30451	304N	80	550	35	240	30	217	95 HRBW	not required
S30452	XM-21 <sup>J</sup>								
Sheet and Strip		90	620	50	345	30	241	100 HRBW	not required
Plate		85	585	40	275	30	241	100 HRBW	not required
S30453	304LN	75	515	30	205	40	217	95 HRBW	not required
S30500	305	70	485	25	170	40	183	88 HRBW	not required
S30530	...	75	515	30	205	40	201	92 HRBW	not required
S30600	...	78	540	35	240	40	...	...	...
S30616	...	86	590	36	245	40	241	100 HRBW	not required
S30601	...	78	540	37	255	30	...	...	not required
S30615	...	90	620	40	275	35	217	95 HRBW	not required
S30815	...	87	600	45	310	40	217	95 HRBW	...
S30908	309S	75	515	30	205	40	217	95 HRBW	not required
S30909	309H <sup>F</sup>	75	515	30	205	40	217	95 HRBW	not required
S30940	309Cb <sup>F</sup>	75	515	30	205	40	217	95 HRBW	not required

## A240/A240M – 20a

TABLE 2 Continued

UNS Designation	Type <sup>A</sup>	Tensile Strength, min		Yield Strength, <sup>B</sup> min		Elongation in 2 in. or 50 mm, min, %	Hardness, max <sup>C</sup>		Cold Bend <sup>D</sup>
		ksi	MPa	ksi	MPa		Brinell. HBW	Rockwell	
S30941	309HCb <sup>F</sup>	75	515	30	205	40	217	95 HRBW	not required
S31008	310S	75	515	30	205	40	217	95 HRBW	not required
S31009	310H <sup>F</sup>	75	515	30	205	40	217	95 HRBW	not required
S31040	310Cb <sup>F</sup>	75	515	30	205	40	217	95 HRBW	not required
S31041	310HCb <sup>F</sup>	75	515	30	205	40	217	95 HRBW	not required
S31050	310 MoLN <sup>F</sup>								
	t ≤ 0.25 in.	84	580	39	270	25	217	95 HRBW	not required
	t > 0.25 in.	78	540	37	255	25	217	95 HRBW	not required
S31060	...	87	600	41	280	40	217	95 HRBW	not required
S31254	...								
	Sheet and Strip	100	690	45	310	35	223	96 HRBW	not required
	Plate	95	655	45	310	35	223	96 HRBW	not required
S31266	...	109	750	61	420	35	...	...	not required
S31277	...	112	770	52	360	40	...	...	not required
S31600	316	75	515	30	205	40	217	95 HRBW	not required
S31603	316L	70	485	25	170	40	217	95 HRBW	not required
S31609	316H	75	515	30	205	40	217	95 HRBW	not required
S31635	316Ti <sup>F</sup>	75	515	30	205	40	217	95 HRBW	not required
S31640	316Cb <sup>F</sup>	75	515	30	205	30	217	95 HRBW	not required
S31651	316N	80	550	35	240	35	217	95 HRBW	not required
S31653	316LN	75	515	30	205	40	217	95 HRBW	not required
S31655	...	92	635	45	310	35	241	100 HRBW	not required
S31700	317	75	515	30	205	35	217	95 HRBW	not required
S31703	317L	75	515	30	205	40	217	95 HRBW	not required
S31725	317LM <sup>F</sup>	75	515	30	205	40	217	95 HRBW	not required
S31726	317LMN <sup>F</sup>	80	550	35	240	40	223	96 HRBW	not required
S31727	...	80	550	36	245	35	217	96 HRBW	not required
S31730	...	70	480	25	175	35	...	90 HRBW	not required
S31753	317LN	80	550	35	240	40	217	95 HRBW	not required
S32050	...	98	675	48	330	40	250	...	not required
S32053	...	93	640	43	295	40	217	96 HRBW	not required
S32100	321	75	515	30	205	40	217	95 HRBW	not required
S32109	321H	75	515	30	205	40	217	95 HRBW	not required
S32615 <sup>K</sup>	...	80	550	32	220	25	...	...	not required
S32654	...	109	750	62	430	40	250	...	not required
S33228	...	73	500	27	185	30	217	95 HRBW	not required
S33400	334 <sup>F</sup>	70	485	25	170	30	...	92 HRBW	not required
S33425	...	75	515	30	205	40	...	...	not required
S33426	t ≤ 0.12 in. [3 mm]	75	515	30	205	30	217	95 HRBW	not required
	t > 0.12 in. [3 mm]	69	475	25	170	35	217	95 HRBW	not required
S33550	...	87	600	41	280	35	217	95 HRBW	not required
S34565	...	115	795	60	415	35	241	100 HRBW	not required
S34700	347	75	515	30	205	40	201	92 HRBW	not required
S34709	347H	75	515	30	205	40	201	92 HRBW	not required
S34751	347LN	75	515	30	205	40	201	92 HRBW	not required
S34752	...	75	515	30	205	35	...	...	not required
S34800	348	75	515	30	205	40	201	92 HRBW	not required
S34809	348H	75	515	30	205	40	201	92 HRBW	not required
S35045	...	70	485	25	170	35	...	...	not required
S35115	...	85	585	40	275	40	241	100 HRBW	not required
S35125	...	70	485	30	205	35	...	...	not required
S35135	...								
	Sheet and Strip	80	550	30	205	30	...	...	not required
	Plate	75	515	30	205	30	...	...	not required
S35140	...	90	620	40	275	30	241	100 HRBW	not required
S35315	...	94	650	39	270	40	217	95 HRBW	not required
S38100	XM-15 <sup>J</sup>	75	515	30	205	40	217	95 HRBW	not required
S38815	...	78	540	37	255	30	...	...	not required
Duplex (Austenitic-Ferritic)									
S31200	...	100	690	65	450	25	293	31 HRC	not required
S31260	...	100	690	70	485	20	290	...	...
S31803	...	90	620	65	450	25	293	31 HRC	not required
S32001	...	90	620	65	450	25	...	25 HRC	not required
S32003	...								

## A240/A240M – 20a

TABLE 2 Continued

UNS Designation	Type <sup>A</sup>	Tensile Strength, min		Yield Strength, <sup>B</sup> min		Elongation in 2 in. or 50 mm, min, %	Hardness, max <sup>C</sup>		Cold Bend <sup>D</sup>
		ksi	MPa	ksi	MPa		Brinell, HBW	Rockwell	
S32101	t ≤ 0.187 in. [5.00 mm]	100	690	70	485	25	293	31 HRC	not required
	t > 0.187 in. [5.00 mm]	95	655	65	450	25	293	31 HRC	not required
	...								
	t ≤ 0.187 in. [5.00 mm]	101	700	77	530	30	290	31 HRC	not required
	t > 0.187 in. [5.00 mm]	94	650	65	450	30	290	31 HRC	not required
S32202	...	94	650	65	450	30	290	31 HRC	not required
S32205	2205 <sup>F</sup>	95	655	65	450	25	293	31 HRC	not required
S32304	2304 <sup>F</sup>	87	600	58	400	25	290	32 HRC	not required
S32506	...	90	620	65	450	18	302	32 HRC	not required
S32520	...	112	770	80	550	25	310	32 HRC	not required
S32550	255 <sup>F</sup>	110	760	80	550	15	302	32 HRC	not required
S32750	2507 <sup>F</sup>	116	795	80	550	15	310	32 HRC	not required
S32760	...	108	750	80	550	25	310	32 HRC <sup>R</sup>	not required
S32808	...	101	700	72	500	15	310	32 HRC	not required
S32900	329	90	620	70	485	15	269	28 HRC	not required
S32906	...	116	800	94	650	25.0	310	32 HRC	not required
	t < 0.4 in. [10.0 mm]								
	t ≥ 0.4 in. [10.0 mm]	109	750	80	550	25.0	310	32 HRC	not required
S32950 <sup>L</sup>	...	100	690	70	485	15	293	32 HRC	not required
S39274	...	116	800	80	550	15	310	32 HRC	not required
S81921	...	90	620	65	450	25	293	31 HRC	not required
S82011	...	101	700	75	515	30	293	31 HRC	not required
	t ≤ 0.187 in. [5.00 mm]								
	t > 0.187 in. [5.00 mm]	95	655	65	450	30	293	31 HRC	not required
S82012	t > 0.187 in. [5.00 mm]	94	650	58	400	35	290		
	t ≤ 0.187 in. [5.00 mm]	102	700	73	500	35		31 HRC	not required
S82013	...	90	620	65	450	30	293	31 <sup>J</sup>	not required
S82031	t > 0.187 in. [5.00 mm]	94	650	58	400	35	290		not required
	t ≤ 0.187 in. [5.00 mm]	102	700	73	500	35		31 HRC	not required
S82121	...	94	650	65	450	25	286	30 HRC	not required
S82122	t < 0.118 in. [3.00 mm]	101	700	72	500	25	290	32 HRC	not required
	t ≥ 0.118 in. [3.00 mm]	87	600	58	400	30	290	32 HRC	not required
S82441	...								
	t < 0.4 in. [10.0 mm]	107	740	78	540	25	290	31 HRC	not required
	t ≥ 0.4 in. [10.0 mm]	99	680	70	480	25	290	31 HRC	not required
Ferritic or Martensitic (Chromium)									
S32803	...	87	600	72	500	16	241	100 HRBW	not required
S40300	403	70	485	30	205	25 <sup>N</sup>	217	96 HRBW	180
S40500	405	60	415	25	170	20	179	88 HRBW	180
S40900 <sup>M</sup>	409 <sup>M</sup>								
S40910	...	55	380	25	170	20	179	88 HRBW	180
S40920	...	55	380	25	170	20	179	88 HRBW	180
S40930	...	55	380	25	170	20	179	88 HRBW	180
S40945	...	55	380	30	205	22	...	80 HRBW	180
S40975	...	60	415	40	275	20	197	92 HRBW	180
S40977	...	65	450	41	280	18	180	88 HRBW	not required
S41000	410	65	450	30	205	20	217	96 HRBW	180
S41003	...	66	455	40	275	18	223	20 HRC	not required
S41008	410S	60	415	30	205	22 <sup>N</sup>	183	89 HRBW	180
S41045	...	55	380	30	205	22	...	80 HRBW	180

## A240/A240M – 20a

TABLE 2 Continued

UNS Designation	Type <sup>A</sup>	Tensile Strength, min		Yield Strength, <sup>B</sup> min		Elongation in 2 in. or 50 mm, min, %	Hardness, max <sup>C</sup>		Cold Bend <sup>D</sup>
		ksi	MPa	ksi	MPa		Brinell. HBW	Rockwell	
S41050	...	60	415	30	205	22	183	89 HRBW	180
S41500	...	115	795	90	620	15	302	32 HRC	not required
S42000	420	100 <sup>O</sup>	690 <sup>O</sup>	...	...	15	217	96 HRBW	not required
S42035	...	80	550	55	380	16	180	88 HRBW	not required
S42200	422	...	...	...	...	...	248	24 HRC	not required
S42900	429 <sup>F</sup>	65	450	30	205	22 <sup>N</sup>	183	89 HRBW	180
S43000	430	65	450	30	205	22 <sup>N</sup>	183	89 HRBW	180
S43035	439	60	415	30	205	22	183	89 HRBW	180
S43037	...	50	360	30	205	22	183	89	180
S43100	431	...	...	...	...	...	285	29 HRC	not required
S43400	434	65	450	35	240	22	...	89 HRBW	180
S43600	436	65	450	35	240	22	...	89 HRBW	180
S43932	...	60	415	30	205	22	183	89 HRBW	180
S43940	...	62	430	36	250	18	180	88 HRBW	not required
S44330	...	56	390	30	205	22	187	90 HRBW	not required
S44100	...	60	414	35	241	20	190	90 HRBW	not required
S44200	442	65	515	40	275	20	217	96 HRBW	180
S44400	...	60	415	40	275	20	217	96 HRBW	180
S44500	...	62	427	30	205	22	...	83 HRBW	180
S44535	...	58	400	36	250	25 <sup>E</sup>	...	90 <sup>O</sup> HRBW	not required
S44536	...	60	410	35	245	20	192	90 HRBW	180
S44537	...	65	450	46	320	18 <sup>P</sup>	200	93 HRBW	180
S44600	446	65	515	40	275	20	217	96 HRBW	135
S44626	XM-33 <sup>J</sup>	68	470	45	310	20	217	96 HRBW	180
S44627	XM-27 <sup>J</sup>	65	450	40	275	22	187	90 HRBW	180
S44635	...	90	620	75	515	20	269	28 HRC	180
S44660	...	85	585	65	450	18	241	100 HRBW	180
S44700	...	80	550	60	415	20	223	20 HRC	180
S44725	...	65	450	40	275	20	210	95 HRBW	180
S44735	...	80	550	60	415	18	255	25 HRC	180
S44800	...	80	550	60	415	20	223	20 HRC	180
S46800	...	60	415	30	205	22	...	90 HRBW	180

<sup>A</sup> Unless otherwise indicated, a grade designation originally assigned by the American Iron and Steel Institute (AISI).

<sup>B</sup> Yield strength shall be determined by the offset method at 0.2 % in accordance with Test Methods and Definitions A370. Unless otherwise specified (see Specification A480/A480M, 4.1.11, Ordering Information), an alternative method of determining yield strength may be based on total extension under load of 0.5 %.

<sup>C</sup> Either Brinell or denoted Rockwell Hardness scale is permissible. For thin materials, see Specification A480/A480M (17.2.1) and Test Methods A370 (18.1.2) on superficial testing.

<sup>D</sup> Bend tests are not required for chromium steels (ferritic or martensitic) thicker than 1 in. [25 mm] or for any austenitic or duplex (austenitic-ferritic) stainless steels regardless of thickness.

<sup>E</sup> Elongation for thickness, less than 0.015 in. [0.38 mm] shall be 20 % minimum, in 1 in. [25.4 mm].

<sup>F</sup> Common name, not a trademark, widely used, not associated with any one producer.

<sup>G</sup> Yield strength requirements shall not apply to material under 0.020 in [0.50 mm] in thickness.

<sup>H</sup> Not applicable for thicknesses under 0.010 in. [0.25 mm].

<sup>I</sup> Type 201 is generally produced with a chemical composition balanced for rich side (Type 201-1) or lean side (Type 201-2) austenite stability depending on the properties required for specific applications.

<sup>J</sup> Naming system developed and applied by ASTM.

<sup>K</sup> For S32615, the grain size as determined in accordance with the Test Methods E112, Comparison Method, Plate II, shall be No. 3 or finer.

<sup>L</sup> Prior to Specification A240 – 89b, the tensile value for S32950 was 90 ksi.

<sup>M</sup> S40900 (Type 409) has been replaced by S40910, S40920, and S40930. Unless otherwise specified in the ordering information, an order specifying S40900 or Type 409 shall be satisfied by any one of S40910, S40920, or S40930 at the option of the seller. Material meeting the requirements of S40910, S40920, or S40930, may at the option of the manufacturer be certified as S40900.

<sup>N</sup> Material 0.050 in [1.27 mm] and under in thickness shall have a minimum elongation of 20 %.

<sup>O</sup> Hardness is required to be provided for information only, but is not required to meet a particular requirement.

<sup>P</sup> The minimum elongation for plates thicker than 0.630 in. [16 mm] shall be 8 %.

<sup>Q</sup> Maximum. Type 420 is usually used in the heat-treated condition (quenched and tempered to a specific range of hardness or tensile strength).

<sup>R</sup> Hardness conversion tables for superduplex stainless steels do not exist in ASTM E140. The conversion value from HBW to HRC has been added to maintain consistency with other ASTM standards for these superduplex stainless steels.